

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C03B 37/03, C03C 25/00		A1	(11) International Publication Number: WO 99/67180
			(43) International Publication Date: 29 December 1999 (29.12.99)
(21) International Application Number: PCT/EP99/04292		(81) Designated States: AU, BR, CA, CN, IN, JP, KR, NZ, RU, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 22 June 1999 (22.06.99)			
(30) Priority Data: 98202098.4 24 June 1998 (24.06.98) EP 60/091,046 29 June 1998 (29.06.98) US		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant (for all designated States except US): PIRELLI CAVI E SISTEMI S.P.A. [IT/IT]; Viale Sarca, 222, I-20126 Milano (IT).			
(72) Inventors; and (75) Inventors/Applicants (for US only): ROBA, Giacomo, Stefano [IT/IT]; Via Arno, 5/10, I-20052 Monza (IT). PATA, Roberto [IT/IT]; Via Partigiani, 10, I-24100 Bergamo (IT).			
(74) Agents: BOTTERO, Claudio et al.; Porta, Checcacci & Associati S.p.A., Viale Sabotino, 19/2, I-20135 Milano (IT).			

(54) Title: METHOD AND APPARATUS FOR TWISTING A COATED OPTICAL FIBER DURING DRAWING FROM A PREFORM

(57) Abstract

A method for manufacturing an optical fiber (100) having low PMD, comprises the steps of: a) heating at least one end portion (3a) of a preform (3); (b) drawing an optical fiber (100) from a free end of said heated end portion (3a) along a fiber drawing axis (I-I); c) coating said optical fiber (100) with a suitable coating material; d) applying to said coated optical fiber (100) a torque about said fiber drawing axis (I-I); e) winding said coated optical fiber (100) onto a collecting spool (9). According to the invention, step d) is carried out by means of a pulley (16) supported upstream of said collecting spool (9) and rotated about the fiber drawing axis (I-I), said optical fiber (100) being wound up onto said pulley (16) for an angle of at least about 360°. Advantageously, such method also allows to notably increase the amount of optical fiber produced per unit of time with respect to the prior art. Disclosed is also an apparatus for carrying out the method and a device for applying torque to the fiber comprising a pulley.



BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

METHOD AND APPARATUS FOR TWISTING A COATED OPTICAL FIBER DURING DRAWING FROM A PREFORM

DESCRIPTION5 FIELD OF THE INVENTION

The present invention relates, in a first aspect thereof, to a method for manufacturing an optical fiber from a preform, comprising the steps of:

- a) heating at least one end portion of said preform;
- 10 b) drawing an optical fiber from a free end of said heated end portion along a fiber drawing axis;
- c) coating said optical fiber with a suitable coating material;
- d) applying to said coated optical fiber a torque about
15 said fiber drawing axis,
- e) winding said coated optical fiber (100) onto a collecting spool (9).

More specifically, this invention relates to a method for manufacturing an optical fiber having low PMD for use in
20 telecommunication field.

The present invention also relates to a device for applying a torque to an optical fiber about its drawing axis, as well as to an apparatus for carrying out the above-mentioned method.

25 PRIOR ART

As is known, in signal transmission systems using optical fibers, above all in those systems operating over long distances, the need arises of minimizing any kind of

- 2 -

attenuation or dispersion of the signals, in order to assure high transmission and reception standards. In particular, the need arises of minimizing a specific dispersion phenomenon known as PMD (Polarization Mode
5 Dispersion), that implies a restriction in the width of the signal transmission band and, accordingly, a worsening in the performances of the optical fibers through which the above-mentioned signals are transmitted.

As is known, the fundamental propagation mode of a signal
10 in an optical fiber may be seen as the resultant of two linearly polarized waves on orthogonal planes. Theoretically, in a perfectly symmetric circular section fiber (i.e., in monomode fibers) the propagation constants of the two components are identical and therefore the mode
15 propagates unaltered and according to a cylindrical symmetry along the fiber itself, with the two components traveling at the same speed. In contrast thereto, however, optical fibers possess in practice structural and geometrical irregularities that, by altering the above-
20 mentioned cylindrical symmetry, bring about asymmetric stress conditions in the fibers themselves and anisotropy in their optical properties; accordingly, the two mode components meet zones with different refraction index and travel with different propagation speeds, thus causing the
25 PMD phenomenon.

A parameter of particular importance in this respect, is the so-called coherence length or fiber beat length, that is, the necessary length of fiber needed for the two components of the fundamental mode to get in phase again
30 with one another.

Other than by structural and/or geometrical defects which are intrinsic in the fiber, such as, for example, the presence of not perfectly circular cores, the PMD phenomenon may also be originated by asymmetric stress
35 conditions caused by outer stresses such as, for example,

- 3 -

those generated in operation during the spool winding or wiring steps.

It has been experimentally shown that it is possible to reduce the PMD of an optical fiber by submitting the latter to suitable external stresses during the drawing process, in particular by applying a torque to such an optical fiber.

To this end, various devices and methods for manufacturing an optical fiber having low PMD have been proposed in the past, the earlier ones based upon the technique of rotating the preform (a technique which was soon abandoned due to the evident technological difficulties and to the impossibility of obtaining high rotational speed), the most recent ones based upon the technique of applying during the drawing process a torque to the fiber about its axis (fiber spinning/twisting).

Therefore, for example, US Patent No. 4,504,000 (Thomson - CSF) discloses a method for manufacturing an optical fiber having a chiralic structure with high circular birefringence, wherein an equipment provided with three pulleys applies to a fiber produced from a heated portion of a preform a torque about the axis thereof. The applied torque is subsequently "frozen" in the fiber structure by means of a suitable coating film, in glass or glass-ceramic, applied on the fiber itself in a dedicated coating station.

A drawback associated to the above disclosed method is connected to the high risk of damaging the fiber surface due to the fact that the latter gets in touch with the above mentioned pulleys before being properly protected by a suitable coating film.

In order to overcome the above mentioned drawback it has been proposed, as disclosed in US Patents No. 5,298,047 and 5,418,881 (AT&T), to arrange the device adapted to apply

- 4 -

the torque to the fiber downstream of the coating station. In particular, in the above mentioned patents, torque is applied by means of a fiber guiding roll having a rotation axis which extends perpendicularly to the drawing axis of the fiber and which is alternatively canting in clockwise and counterclockwise direction.

Although substantially achieving the object of reducing the PMD of the fiber, the Applicant has however noticed that the above disclosed method shows a series of drawbacks to which no adequate solution has been given up to now.

A first drawback observed by the Applicant is connected to the need of limiting the canting frequency of the guiding roll in order to avoid that, during the drawing process, a relative sliding between the optical fiber and the roll could take place. Actually, there are two reasons for such a sliding to be particularly disadvantageous: firstly because it could cause a mechanical abrasion of the optical fiber surface and, accordingly, a worsening of the mechanical resistance properties and of the performances of the fiber itself; secondly, because it does not allow the torque to be imparted to the optical fiber according to a desired law of variation, thus limiting the advantageous effects given by the applied twisting regarding the reduction of the PMD phenomenon.

The limitation of the canting frequency of the guiding roll implies, furthermore, a corresponding limitation in the drawing speed of the fiber (the two speeds being unavoidably related to one another in order to apply the desired torque to the fiber) and, therefore, a limitation in the amount of fiber produced per unit of time.

A further drawback associated with the above disclosed method is connected to the fact that the oscillations of the fiber during the drawing may induce displacements of the drawing axis which cause undesired fluctuations in the diameter of the fiber produced or unevenness and/or

- 5 -

imperfect coaxiality between the fiber and the coating layer applied thereon.

Furthermore, such method does not allow to apply a continuous unidirectional rotation to the optical fiber, because the device which is used necessarily imparts an alternate twisting to the optical fiber.

Other methods are known for the manufacture of optical fibers, comprising the step of applying a torque to the fiber about its drawing axis and "freezing" the applied torque by means of a suitable coating film before the fiber reaches the twisting means are also disclosed by Japanese Patent Application No. JP 58-020746 and by German patent DE 3010005.

JP 58-020746 discloses a method for the manufacture of optical fibers adapted to maintain a single mode circular polarization of the fiber, that is a method wherein the plane of polarization is uniformly rotated across the length of the fiber itself. In order to produce the birefringence required for the circularly polarized mode, the fiber is drawn from the free end of the preform by drawing means located upstream of the coating station and the twist is imparted to the fiber by means of a collecting spool located downstream of a coating station.

Similarly, German Patent DE 3010005 discloses a method for the manufacture of twisted optical fibers wherein the fiber is drawn and twisted by means of a collecting spool located downstream of a number of coating stations.

According to the above disclosed methods, the twist is however imparted to the solidified fiber in the region between said drawing means and said collecting spool, being thus prevented from reaching the softened bottom end of the preform.

A further drawback associated to the above disclosed method

- 6 -

is connected to the high mass and inertia of the collecting spool used for imparting the torque to the fiber, which does not allow to increase the rotation speed of the spool (and hence the drawing speed of the fiber), as well as to
5 reliably apply a desired law of torque variation to the fiber. Besides, there is the need of translating the spool (or providing suitable means) for allowing the fiber be collected thereon.

Finally, Japanese Patent Application No. JP 06-239642
10 discloses a method for the manufacture of optical fiber bundles, wherein a twist is imparted to a number of fibers in order to obtain helically twisted fibers which, once they are collected together to form a bundle, have ends randomly positioned at the incident and emergent sides of
15 the bundle. The twist is imparted, for example, by a caterpillar located upstream of the collecting spool; the caterpillar is also used to draw the fiber from the preform.

The object of the above disclosed method is quite different
20 from the one of the present invention. In fact, for achieving the above mentioned object, fibers having a helical extension along the axial direction are manufactured.

Also in this case and because of the high mass and inertia
25 of the caterpillar used for imparting the torque to the fiber, however, it is not possible to increase the rotation speed of the caterpillar (and hence the drawing speed of the fiber) as well as to reliably apply to the fiber a desired law of torque variation.

30 SUMMARY OF THE INVENTION

The applicant has now discovered a method and an apparatus that allow the manufacture of an optical fiber having low PMD, while overcoming at the same time the above mentioned drawbacks of the cited prior art.

- 7 -

- According to a first aspect thereof, the present invention relates to a method of the type mentioned hereinabove, which is characterized in that the application to the above mentioned coated fiber of the torque about the drawing axis of the fiber is carried out by means of a pulley which is supported upstream of the collecting spool and rotated about the drawing axis of the fiber and on which said optical fiber is wound up with an angle substantially equal to at least 360° .
- 10 Advantageously, the method of the present invention allows to achieve the desired fiber twisting without compromising its properties of mechanical resistance and, in the meantime, allows to obtain a high drawing speed for the same, thus increasing the production of optical fiber per
- 15 unit of time. Differently from the known methods, in fact, in the method according to the present invention the fiber is wound up for at least about 360° and in substantial absence of sliding onto a member adapted to apply the desired twisting to the fiber itself (pulley); this allows
- 20 to increase the rotation speed of the pulley itself (and hence the drawing speed of the fiber) without incurring in the risk of having relative sliding between the pulley and the fiber. Further on, the absence of such sliding allows to apply to the fiber the desired law of torque variation.
- 25 Advantageously, the absence of any form of oscillation also allows to avoid any interference with the step of applying the coating layer onto the fiber, whereby the layer is thus homogeneously distributed over the entire surface of the fiber.
- 30 The above mentioned pulley may be rotated about the drawing axis of the optical fiber according to a unidirectional movement, with a constant or varying rotation speed, such as by way of example a speed varying according to a sinusoidal pattern from a maximum value down to a minimum
- 35 value, which may eventually be equal to zero.

- 8 -

Alternatively, the above mentioned pulley may be rotated about the drawing axis of the optical fiber according to an alternate movement, in clockwise and counterclockwise direction, respectively. In this instance as well, it may
5 be foreseen a constant rotation speed, by applying such speed first according to a spin direction, then reversing the spin direction and applying the same speed value in the opposite direction. A varying speed pattern will instead consist of a speed variation, for example according to a
10 sinusoidal pattern, from a maximum value in one direction to a maximum value in the opposite direction, passing through a zero speed value at the point in which the inversion of rotation takes place.

Advantageously, an alternating rotation speed is applied to
15 the pulley. This allows to prevent the presence of residual torsions on the fibers wound onto the collecting spool (i.e. the collected fiber is substantially torsion-free), thus making easier both the unwinding and wiring operations of the same.

20 In the following description and in the appended claims, the term: "twisting pitch" is used to indicate the linear distance measured along the outer surface of the fiber between two sections thereof to which the same rotation pattern is imparted.

25 Preferably, the optical fiber is drawn from the preform in a way known per se, though it is in this case possible to apply a drawing speed of the fiber considerably higher than that achievable by the devices of the prior art. This allows to achieve a considerable increase of optical fiber
30 production per time unit. Compatibly with the other components in the drawing system, with the method of the present invention it is in fact possible to apply a drawing speed of, by way of example, 15 m/sec, 20 m/sec, 25 m/sec or even 30 m/s, without any undesired effects on the
35 twisting of the fiber.

- 9 -

In any case, it should be noted that the above mentioned limit value for the drawing speed of the fiber is related to the drawing techniques actually employed, and is not determined by the structural features of the twisting device whereon the pulley is installed.

In a second aspect thereof, the present invention relates to a device for applying to an optical fiber, drawn at a predetermined speed from a heated end of a preform, a torque about a fiber drawing axis thereof, characterized in that it comprises an idle-mounted pulley which is rotated about said axis by respective driving means, said optical fiber being wound up onto said pulley for an angle substantially equal to at least 360.

Advantageously, the device of the present invention is particularly simple from a constructional point of view and has a low cost.

Preferably, the driving means of the device of the present invention is adapted to rotate the pulley about the fiber drawing axis both in a unique direction, and in clockwise and counterclockwise direction, alternately.

Preferably, the above mentioned driving means of the pulley comprises a motor-driven fork-shaped supporting member, having a rotation axis coincident with the fiber drawing axis and whereon the pulley is pivoted in an offset position, in such a way as to be substantially tangent to said axis. The drawing directions of the fiber immediately upstream and downstream of the pulley are therefore identical, thus assuring the absence of misalignment conditions that cause undesired fluctuations in the diameter of the fiber produced and unevenness in the applied coating film.

Advantageously, the driving means of the pulley comprises an electric motor kinematically connected to the pulley, i.e., by means of a belt transmission system.

- 10 -

Advantageously, the reduced weight and the small size of the pulley limit the magnitude of the inertial forces acting on the device during twisting; in such a way, it is possible to achieve rotational speeds which are considerably higher than those of the devices of the prior art, although motors are employed which have less power and a lower cost.

The winding process of the fiber onto the pulley substantially made in the absence of sliding therebetween, is facilitated if the pulley is provided with a suitable profile. In a first embodiment, the pulley is provided with a substantially V-shaped groove, adapted to receive the optical fiber, which comprises opposite side walls forming an angle φ in the range between 65° and 75° with the plane of symmetry π of the pulley.

In a particularly advantageous embodiment, the groove comprises opposite side walls having a first radially outer portion forming an angle φ_1 in the range between 65° and 75° with the plane of symmetry π of the pulley and a second radially inner portion forming an angle φ_2 in the range between 25° and 35° with said plane of symmetry π . Preferably, said first and second portions of the side walls are reciprocally connected by means of an intermediate portion having a radius of curvature in the range between 0 and 2 mm. Such a profile advantageously allows to facilitate the winding and unwinding steps of the fiber onto and from the pulley, respectively.

Preferably, the groove comprises a bottom surface which is essentially planar, or anyway having a radius of curvature considerably larger than the radius of the optical fiber, in such a way that the contact between the fiber and the bottom surface and one of the side walls, respectively, is essentially reduced to a point in cross section. If the fiber is wound up onto the pulley for an angle substantially equal to 360° , the bottom surface of the

- 11 -

groove will also have a width adapted to allow for the simultaneous housing of two fiber portions lying side-by-side (respectively associated to a new portion of fiber entering into the pulley and to the portion of fiber
5 leaving the pulley).

Preferably, the pulley is made of a suitable material adapted to develop with the optical fiber a coefficient of friction capable to assure a substantial absence of sliding during the winding up of the fiber onto the pulley. Even
10 more preferably, such coefficient of friction is greater than about 0.4. In this way, it is possible to carry out a fiber twisting without compromising its properties of mechanical resistance, even for values of drawing force smaller than those applicable in the devices of the prior
15 art.

In a third aspect thereof, the present invention relates to an apparatus for manufacturing an optical fiber from a preform, comprising:

- means for heating at least one end portion of said
20 preform;
- means for drawing an optical fiber from a free end of said heated end portion along a fiber drawing axis;
- at least one coating station of said optical fiber;

characterized in that it comprises, downstream said at
25 least one coating station, a device of the type described hereinabove.

BRIEF DESCRIPTION OF THE DRAWINGS

Further features and advantages of the present invention will become more readily apparent from the following
30 detailed description of a preferred embodiment thereof, given hereinbelow by way of illustrative and non limitative example, reference being made to the accompanying drawings.

- 12 -

In such drawings:

- Figure 1 is a schematic view of an apparatus for manufacturing an optical fiber according to the invention;
- Figure 2 is a perspective view, in partial cross-section, of a device according to the present invention for applying a torque to an optical fiber;
- Figure 3 is a perspective view, in an enlarged scale and in partial cross-section, of a pulley mounted on the device of Fig. 2 and shown in an operative condition thereof;
- Figure 4 is a perspective view, in an enlarged scale, of a portion of the pulley of fig. 3, shown in partial cross-section.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

- 15 In Figure 1, numeral 1 indicates an apparatus for manufacturing an optical fiber according to the present invention.

The apparatus 1 comprises a furnace 2 known *per se*, adapted to heat an end portion 3a of a silica-based preform 3, of conventional type as well, having a diameter in the range between about 2 and about 12 cm. Drawing means 4 (of known type as well) are provided downstream of the furnace 2 for drawing at a predetermined speed an optical fiber 100 from the end 3a of the preform 3 along a drawing axis I-I.

- 25 The apparatus 1 is provided, between the furnace 2 and the drawing means 4, with a device 5 for cooling the fiber 100, known *per se*, adapted to adjust the temperature of the fiber 100 at the inlet of a first coating station 6, wherein a first layer of protective film, typically consisting of an acrylic resin, is applied (the presence of the cooling device 5 is particularly advantageous mainly in very high speed drawing processes). A UV-ray furnace 7 for

- 13 -

crosslinking the applied resin and another pair of coating station 6'/UV-ray furnace 7', respectively designed to apply and subsequently crosslink a second layer of protective film, this latter typically consisting of an acrylic resin as well, are provided downstream of the first coating station 6. The overall thickness of the coating applied on the fiber 100 by the two coating stations 6, 6' is typically equal to about 62,5 μm .

A twisting device 8 adapted to impart to the coated optical fiber 100 a torque about the drawing axis I-I is provided downstream of the furnace 7'.

The apparatus 1 further comprises a spool 9 for collecting the produced optical fiber 100, located downstream of the drawing means 4. The collecting spool 9 is stationary with respect to the drawing axis I-I of the optical fiber 100 and rotatably driven about its axis by suitable motor means in order to allow the optical fiber 100 to be wound thereon.

As shown in figure 2, the twisting device 8 comprises a pulley 16 rotatably driven about the drawing axis I-I of the optical fiber 100 by a driving group 12 supported by a supporting plate 11 of a framework 10 by means of an intermediate plate 13 interposed therebetween.

Advantageously, the intermediate plate 13 is slidably mounted on a pair of slideways 14 fastened to the supporting plate 11, so that the pulley 16 and its driving group 12 may be adjustably positioned towards and away from the drawing axis I-I of the optical fiber 100.

The pulley 16 is rotatably idle-mounted in an offset position on a forked-shaped member 15 of the driving group 12, so as to result substantially tangent to the drawing axis I-I of the optical fiber 100.

In order to rotatably drive the pulley 16, the driving

- 14 -

group 12 further comprises motor means 17, kinematically connected to the fork-shaped member 15, in such a way as to transmit to the latter a rotating movement about a rotation axis coincident with the fiber drawing axis I-I.

- 5 More specifically, the fork-shaped member 15 is fastened to a pin 18 on which a driven pulley 19, kinematically connected by means of a belt 20 to a driving pulley 21 keyed on a shaft 32 of the motor means 17, is fastened.

10 The pin 18 and the pulley 19 are mounted in a manner known *per se* inside a substantially cylindrical box-shaped protection body 22 fixed to the plate 13. The rotation of the pin 18 about the rotation axis I-I is guided by a pair of roll bearings 23, 24 respectively associated to the box-shaped body 22 and to the plate 13.

- 15 The pin 18 is axially provided with a through bore 25 adapted to allow the passage of the optical fiber 100 leaving the pulley 16.

20 Figures 3 and 4 show, in greater detail, the structural features of the pulley 16. This pulley is provided with a substantially V-shaped groove 26 adapted to receive during its operation the optical fiber 100 to be twisted.

The groove 26 comprises a substantially planar bottom surface 27 (or anyway having a radius of curvature considerably greater than the radius of the fiber 100, which typically is equal to about 125 μm), connecting opposite side walls 28a, 28b. The bottom surface 27 has a width adapted to receive at one and the same time two portions of the fiber 100 lying side-by-side (associated to the portion of fiber 100 entering the pulley 16 and leaving the pulley 16, respectively).

According a preferred embodiment and in order to facilitate the introduction of the optical fiber 100 into the groove 26, each side wall 28a, 28b is provided with a first

- 15 -

radially outer portion 29a and 29b, forming with the plane of symmetry π of the pulley 16 an angle φ_1 in the range between 65° and 75° , and a second radially inner portion 30a, 30b forming with the above mentioned plane of symmetry π an angle φ_2 in the range between 25° and 35° . Preferably, the angle φ_1 is about 70° , whereas the angle φ_2 is about 30° .

The portions 29a, 29b are connected to the portions 30a, 30b by means of an intermediate portion 31a, 31b having a radius of curvature in the range from 0 to 2 mm.

Advantageously, the pulley 16 is made of a suitable material adapted to generate with the optical fiber 100 a coefficient of friction greater than about 0.4, so as to assure a substantial absence of sliding during the winding up of the fiber 100 onto the pulley 16. Preferably, such material is a metallic material, such as for instance steel or aluminum, having a coefficient of friction of about 0.6.

To reduce the moment of inertia and the loss of balance of the pulley while rotating about the axis of the fiber, it is particularly advantageous to use a sufficiently light material for the construction of such pulley, such as for example aluminum. On the other end, particularly if the use of a heavier material is desired, such as for example steel, it may be advantageous to use a suitable counterweight for the structure that bears the pulley, with the objective to minimize the loss of balance of the pulley during its rotation. Typically, such counterweight is symmetrically arranged with respect to the pulley referring to the fiber drawing axis, in order to counterbalance the rotating pulley mass. Advantageously, such counterweight could be integral with the supporting member (15) on which the pulley is pivoted. In particular, the supporting member may be provided with such a shape and size as to obtain a proper mass distribution in order to balance the rotating pulley mass, making the center of mass of the structure:

- 16 -

pulley-supporting member, coincident with the point where the optical fiber is tangent to the groove of the pulley.

The above described pulley preferably has a diameter in the range from about 30 mm to about 100 mm, a diameter equal to
5 about 60 mm being particularly preferred.

With reference to apparatus 1 described hereinabove, a method for manufacturing an optical fiber according to this invention will now be disclosed.

10 In order to simplify the description hereinbelow, reference will be made to the operating steps of the method while already in steady conditions, thus disregarding the start-up steps of the manufacturing process.

In a first step of the method, the portion 3a of the silica-based preform 3 is heated in the furnace 2, so as to
15 melt the silica-based material and forming an optical fiber 100 having a diameter of about 125 μm .

Thereafter, the optical fiber 100 formed from the heated end portion 3a of the preform 3 is drawn by the drawing means 4 at a predetermined speed, preferably in the range
20 of about 15 m/s.

In a following step, the optical fiber 100 is first cooled in the cooling device 5 and then coated with a suitable protective film, consisting by way of example of acrylic resin having a thickness of about 62,5 μm upon passing
25 through the coating stations 6, 6' and the UV-ray furnaces 7 and 7' for crosslinking the applied resin.

According to the invention, a torque varying according to a predetermined law of variation is subsequently applied to the so coated optical fiber 100 by means of the pulley 16
30 of the twisting device 8.

In a preferred embodiment, the pulley 16 is rotated about the fiber drawing axis I-I by the motor means 17. The

- 17 -

rotation speed of the pulley 16 may be constant or varying, and according to a unidirectional or alternate movement in clockwise and counterclockwise direction, respectively; in an alternative embodiment, the rotation speed of the pulley 16 may vary in a random way.

In such step, the optical fiber 100 is wound up on the pulley 16 while being continuously kept in contact with the bottom surface 27 of the pulley 16 for an angle substantially equal to about 360° , in such a way that the fiber is wound up on the pulley for about a complete turn. If desired, it is possible to wind the fiber up about the pulley for a number of turns greater than one, that is for an angle greater than 360° , for instance for an angle equal to about 720° corresponding to a winding of about two turns of fiber about the pulley. A winding of the optical fiber about the pulley for a number of turns greater than one, by increasing the contact surface between the optical fiber and bottom surface of the pulley, allows to use a pulley consisting of material with a relatively low coefficient of friction, in particular smaller than about 0.4.

In any case, it would be preferable to wind up the fiber around the pulley for an angle not exceeding 720° , so that the fiber is not subjected to an undesirably high drawing tension.

The fiber 100 is further partially in contact with one of the two side walls 28a, 28b and, on the other side, with a small portion of new optical fiber 100 entering the pulley 16 and moving in the same direction and with a speed equal to that possessed by the fiber leaving the pulley. Therefore a torque is applied to the optical fiber 100, which is capable to compensate the imperfections and irregularities which are inherently present in the fiber itself or which are generated during the subsequent manufacture of a cable which contains such fiber and/or during its wiring, thus considerably reducing the PMD

- 18 -

phenomenon.

In a final step of the method, the twisted optical fiber 100 leaving the pulley 16 crosses the through bore 25 of the pin 18, which coaxially extends along the fiber drawing
5 axis I-I and reaches the drawing means 4 from which the fiber is delivered to the collecting spool 9.

*** * ***

The various advantages of the present invention with respect to the prior art are immediately evident from the
10 description reported hereinabove.

Firstly, the method of the present invention allows to notably increase the drawing speed of the optical fiber without incurring in the risk of having relative sliding between the pulley 16 and the fiber 100, thus increasing
15 the amount of optical fiber produced per unit of time.

Thanks to the reduced inertia of the pulley 16 and of the moving parts of the driving group 12, moreover, it is possible not only to effectively apply the desired law of torque variation to the optical fiber 100, minimizing at
20 the same time the risk of losing the twist effect, but also to use motors 17 of reduced power and cost with respect to those used in the prior art.

Advantageously, the method of the invention also allows to apply the desired number of twists to the optical fiber 100
25 in substantial absence of oscillations of the fiber about its own drawing axis I-I; this allows a greater uniformity both of the fiber diameter and of the thickness of the coating layer applied thereon.

Lastly, the structural features of the pulley 16 allow both
30 to facilitate the winding and unwinding steps of the optical fiber 100, and to adopt drawing forces which are smaller than those used in the devices of the prior art with a proper choice of the material which constitutes the

pulley itself.

- 20 -

CLAIMS

1. A method for manufacturing an optical fiber from a preform (3), comprising the steps of:
 - a) heating at least one end portion (3a) of said preform
5 (3);
 - b) drawing an optical fiber (100) from a free end of said heated end portion (3a) along a fiber drawing axis (I-I);
 - c) coating said optical fiber (100) with a suitable coating material;
 - 10 d) applying to said coated optical fiber (100) a torque about said fiber drawing axis (I-I),
 - e) winding said coated optical fiber (100) onto a collecting spool (9),characterized in that step d) is carried out by means of a
15 pulley (16) supported upstream of said collecting spool (9) and rotated about said fiber drawing axis (I-I), said optical fiber (100) being wound up onto said pulley (16) for an angle of at least about 360°.
2. The method according to claim 1, wherein said pulley
20 (16) is rotated about said fiber drawing axis (I-I) at a constant rotation speed.
3. The method according to claim 1, wherein said pulley (16) is rotated about said fiber drawing axis (I-I) at a varying rotation speed.
- 25 4. The method according to claim 3, wherein said pulley (16) is rotated about said fiber drawing axis (I-I) alternately in clockwise and counterclockwise direction.
5. A method for manufacturing an optical fiber from a preform (3), comprising the steps of:

- 21 -

a) heating at least one end portion (3a) of said preform (3);

b) drawing an optical fiber (100) from a free end of said heated end portion (3a) along a fiber drawing axis (I-I);

5 c) coating said optical fiber (100) with a suitable coating material;

d) applying to said coated optical fiber (100) a torque about said fiber drawing axis (I-I),

10 characterized in that the optical fiber (100) is drawn from the preform (3) at a drawing speed greater than 15 m/s.

6. A device for applying to an optical fiber (100), drawn at a predetermined speed from a heated end (3a) of a preform (3), a torque about a drawing axis (I-I) thereof, characterized in that it comprises an idle-mounted pulley
15 (16) which is rotated about said drawing axis (I-I) by respective driving means (12), said optical fiber (100) being wound up onto said pulley (16) for an angle substantially equal to at least 360°.

7. The device according to claim 6, further comprising
20 means (17) for rotating said pulley about the fiber drawing axis (I-I) alternately in clockwise and counterclockwise direction.

8. The device according to claim 6, wherein said driving means (12) comprises a motor-driven fork-shaped supporting
25 member (15), having a rotation axis coincident with the drawing axis (I-I) of the fiber and on which said pulley (16) is pivoted in an offset position, in such a way as to be substantially tangent to said axis (I-I).

9. The device according to claim 6, wherein said pulley
30 (16) is provided with a substantially V-shaped groove (26) for receiving said optical fiber (100).


- 22 -

10. The device according to claim 9, wherein said groove (26) comprises opposite side walls (28a, 28b) forming with a plane of symmetry (π) of the pulley (16) an angle (φ) in the range between 65° and 75° .
- 5 11. The device according to claim 9, wherein said groove (26) comprises opposite side walls (28a, 28b) having a first radially outer portion (29a, 29b) forming with a plane of symmetry (π) of the pulley (16) an angle (φ_1) in the range between 65° and 75° and a second radially inner
10 portion (30a, 30b) forming with said plane of symmetry (π) an angle (φ_2) in the range between 25° and 35° .
12. The device according to claim 11, wherein said first and second portion (29a, 29b, 30a, 30b) of said side walls (28a, 28b) are reciprocally connected by means of an
15 intermediate portion (31a, 31b) which has a radius of curvature in the range between 0 and 2 mm.
13. The device according to claim 9, wherein said groove (26) comprises a substantially planar bottom surface (27).
14. The device according to claim 6, wherein said pulley
20 (16) is made of a suitable material adapted to develop with said optical fiber (100) a coefficient of friction which assures a substantial absence of sliding during the winding up of the fiber (100) onto the pulley (16).
15. The device according to claim 14, wherein said
25 coefficient of friction is greater than about 0,4.
16. An apparatus (1) for manufacturing an optical fiber (100) from a preform (3), comprising:
- means (2) for heating at least one end portion (3a) of said preform (3);
 - 30 - means (4) for drawing an optical fiber (100) from a free end of said heated end portion (3a) along a fiber drawing axis (I-I);

- 23 -

- at least one coating station (5, 6) of said optical fiber (100);
 - a spool (9) for collecting said coated optical fiber (100),
- 5 characterized in that it comprises, downstream of said at least one coating station (5, 6) and upstream of said spool (9), a twisting device (8) of the fiber (100) according to anyone of claims 6 to 15.

1/3






FIG. 2

3/3




FIG. 4




FIG. 3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/04292

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C03B37/03 C03C25/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C03B C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 7, no. 91 (C-162), 15 April 1983 (1983-04-15) & JP 58 020746 A (NT&T CORP.), 7 February 1983 (1983-02-07) abstract	1,6,16
A	DE 30 10 005 B (LICEBTIA-PATENT-VERWALTUNGS-GMBH) 12 February 1981 (1981-02-12) column 2, line 48 -column 3, line 15; figure 1	1,6,16



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 October 1999

Date of mailing of the international search report

27/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Stroud, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/04292

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 18, no. 625 (C-1279), 29 November 1994 (1994-11-29) & JP 06 239642 A (FUJIKURA LTD.), 30 August 1994 (1994-08-30) abstract ----	1,6,16
A	EP 0 078 733 A (THOMSON-CSF) 11 May 1983 (1983-05-11) figure 4 ----	1,6
A	EP 0 795 521 A (SUMITOMO ELECTRIC INDUSTRIES, LTD.) 17 September 1997 (1997-09-17) figures 5-10 ----	1,6
A	WO 97 26221 A (CORNING INC.) 24 July 1997 (1997-07-24) figure 17 ----	1,6
A	WO 97 22897 A (CORNING INC.) 26 June 1997 (1997-06-26) figure 5 ----	1,6
A	WO 97 07067 A (PLASMA OPTICAL FIBRE B.V.) 27 February 1997 (1997-02-27) figures 1,2 ----	1,6
A	EP 0 744 636 A (AT&T IPM CORP.) 27 November 1996 (1996-11-27) figures 1-4 ----	1,6
A	EP 0 729 919 A (SUMITOMO ELECTRIC IND., LTD.) 4 September 1996 (1996-09-04) figures 3-10 ----	1,6
A	EP 0 582 405 A (AT&T CO.) 9 February 1994 (1994-02-09) cited in the application figures 1,3-5 -----	1,6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/04292

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 58020746	A	07-02-1983	JP 1590765 G JP 2011532 B	30-11-1990 14-03-1990
DE 3010005	B	12-02-1981	NONE	
JP 06239642	A	30-08-1994	NONE	
EP 0078733	A	11-05-1983	FR 2515693 A JP 58088135 A US 4427717 A	06-05-1983 26-05-1983 24-01-1984
EP 0795521	A	17-09-1997	JP 9243833 A	19-09-1997
WO 9726221	A	24-07-1997	AU 1579497 A CA 2242989 A CN 1209793 A EP 0876305 A JP 11508221 T	11-08-1997 24-07-1997 03-03-1999 11-11-1998 21-07-1999
WO 9722897	A	26-06-1997	US 5704960 A AU 705950 B AU 1288097 A CA 2210470 A CN 1176005 A EP 0811176 A JP 11501133 T US 5822487 A	06-01-1998 03-06-1999 14-07-1997 26-06-1997 11-03-1998 10-12-1997 26-01-1999 13-10-1998
WO 9707067	A	27-02-1997	CN 1166165 A EP 0785913 A JP 10507438 T US 5897680 A	26-11-1997 30-07-1997 21-07-1998 27-04-1999
EP 0744636	A	27-11-1996	CA 2172747 A CN 1159589 A JP 9002834 A	25-11-1996 17-09-1997 07-01-1997
EP 0729919	A	04-09-1996	JP 8295528 A AU 690414 B AU 4584296 A	12-11-1996 23-04-1998 05-09-1996
EP 0582405	A	09-02-1994	US 5298047 A CA 2098747 A,C CN 1083449 A,B JP 6171970 A MX 9304583 A US 5418881 A	29-03-1994 04-02-1994 09-03-1994 21-06-1994 28-02-1994 23-05-1995